
ROC 250

A BASIC APPROACH TO FIGHT AGAINST THE WEAR PHENOMENON

- Wear resistant plates & sheets depending the thickness.
4 - 10 mm: from strip mill, > 10 mm: from quarto mill.

Chemical composition

C	Mn	Si	S	P	Cr
≤ 0.25	≤ 1.85	≤ 0.60	≤ 0.035	≤ 0.035	≤ 1.20

Delivery condition

- **Hardness:**
200 - 260 HB.

- **Delivery condition:**
Normalised / Normalised + tempered.

- **Thickness range:**
4 - 40 mm.

- **Size range:**
 - Width: 1500 - 3000 mm;
 - Length: 6000 mm.

General note

- If further informaton is required, please request a copy of our technical guide.

Contact

- A.** Arley Road, Saltley, Birmingham B8 1BB, United Kingdom
- T.** +44 121 326 3100
- F.** +44 121 326 3105
- E.** a.uk@abraservice.com
- W.** www.abraservice.com/uk/